



# AEROFLEX®



## THE IDEAL EPDM THERMAL INSULATION

### ADVANTAGES

- ◆ Closed cell elastomeric foam
- ◆ Temp. range: -57° C to 125° C
- ◆ Excellent Fire resistance
- ◆ Least Smoke Density & Toxicity
- ◆ Non-polar
- ◆ CFC/ HCFC free
- ◆ Low thermal conductivity
- ◆ Anti-microbial
- ◆ Non-corrosive

### CERTIFICATIONS



## PRODUCT DESCRIPTION

AEROFLEX is a closed cell flexible elastomeric foam made from EPDM rubber. This material has low thermal conductivity and high water vapour diffusion resistance. It is CFC/HCFC, dust & fiber free. It ensures energy saving in eco friendly manner. This product meets insulation requirement in diverse fields such as the automobile, air conditioning & refrigeration industry, construction industry, pharma industry, hotel/ hospital and cold storage industry.

Applications	Insulation to prevent condensation and reduce energy loss on HVAC ducts, pipes, tanks & equipments.
Assembly	Aeroflex can be used together with ALP Aeroflex adhesives (Aerostick) for a complete insulation system.
Product Range*	Available in plain and self-adhesive rolls (sheets) in 9, 13, 16, 19, 25, 32 mm thickness of 1000 mm wide rolls

## TECHNICAL DETAILS

PROPERTIES	VALUES	TEST METHOD
Thermal Insulation Material	Closed Cell Elastomeric EPDM Rubber Foam	
Density	40 to 60 Kg/m <sup>3</sup>	ASTM D 1667
Service Temperature	-57°C to 125° C**	
Thermal Conductivity	0.0330 W/m <sup>2</sup> K at 0°C, 0.0356 W/m <sup>2</sup> K at 24°C 0.0366 W/m <sup>2</sup> K at 32°C	ASTM C 518
<b>Fire &amp; Smoke Characteristics</b>		
a) Flammability	Class V-0	UL 94-1997
b) Flame Spread & Smoke Density Test	Class A (25/50)	ASTM-E84
c) Smoke and Toxicity Test	Passed	IMO FTP Code 2010
d) Self Extinguishing	Passed	ASTM D 635 -18
Water absorption (%)	<5% (by weight)	ASTM D 1056
Water Vapour diffusion resistance Index	≥7000	ASTM E 96
Mold Resistance	Meets Requirement (Rating 1)	UL 181
Fungi Resistance	No Growth	ASTM C 1338
Ozone Depleting substances (CFC/HCFC)	Not Detected	USEPA 5021A / USEPA 8260C
Ozone Resistance	No Cracks	ASTM D 1149
UV Weather Resistance	Excellent	ASTM G154
Flexibility	Excellent ( No rupture)	ASTM C 534
N - Nitrosamines Release	Not Detected	FDA CPG 7117.11
Corrosion on copper, stainless steel	Non Corrosive	DIN 1988
ROHS	Not Detected	EN Restriction of the use of hazardous substances directive (ROHS) 2002/95/EC



### Notes:

\*3mm sheet is available with one side skin only

\*\* Becomes hard at -57° C but can be used at -200° C

- Tolerance for thickness from 6mm to 19mm ±1mm & for 25mm & 32mm ±2mm. Also EPDM HT sheet/ tubes are available for high temp application upto 150° C

**DOWNLOAD  
CATALOGUE**



AAIPL-AEPDM-PC-120522

**ALP AEROFLEX INDIA PVT. LTD.**

Corporate Office: Plot No. 32, Sector-18 HUDA, Gurgaon, Haryana - 122015 (INDIA)

+91-124-4731500    marketing@alpaeroflex.com    www.alpaeroflex.com

Disclaimer: Although these values represent actual results achieved in tests, they should only be used as a guide. ALP Aeroflex cannot guarantee the performance of the product as all situations are different & should be treated separately. All statements & Technical informations are based on results obtained under typical conditions. It is the responsibility of the recipient to verify with us that the informations are appropriate for specific use intended by the recipient.